

HS30

Version No.2

Revision Date: 19/7/2013

Page 1 of 2

DESCRIPTION

HS30 is a neutral cure, low modulus, solvent free, one part, moisture cure, multipurpose sealant and adhesive based on Hodgson Hybrid Polymer Technology with very high strength and superior extension.

KEY FEATURES

Solvent & Isocyanate free.

Gunnable at +5 to +40°C

Does not contain any Phthalates or other harmful plasticisers.

Non corrosive

Excellent primerless adhesion to most substrates.

Weatherable and UV stable.

High strength.

Low odour.

High movement capacity.

Permanantly flexible.

Extended open time, for tooling.

Cures tack free and highly elastic.

Fast curing.

Excellent storage stability.

Highly resistant to substances such as mineral oils and mild solvents, acids and alkalis.

Good tooling properties.

USES

Suitable for many substrates including; unprimed metals, aluminium, steel, composite panels, wood, glass, plastics, concrete, mortar, plaster, epoxy and polyester coated panels, PVCu, polycarbonate, PU, stainless steel, anodised aluminium, copper, zinc, lead, finished wood and polystyrene.

For factory, on-site or remedial applications.

Sealing of construction joints.

All purpose sealant, for internal and external use.

Paintable connection joints.

LIMITATIONS

Do not use for aquaria construction

Do not use with plastics such as; PP, PE, PTFE or other low surface energy materials.

Not for use with bitumen, marble or natural stone.

Not suitable for glazing applications.

HS30

Version No. 2

Revision Date: 19/07/2013

Page 2 of 2

PERFORMANCE

Adhesion: Excellent.

Base technology: Hodgson Hybrid Polymer.

Chemical Resistance: Good.

Curing system: Moisture Cure

Hardness: Shore A = 35

Skin formation: 20 – 40min @ 23°C / 50% RH.

Elongation at break: 600%

Paintability: Paintable with most paints, alkyd based paints may slow curing (testing is recommended).

Density: 1.4g/ml

Extrusion rate: 15-30g/10s

Modulus at 100% elongation: 0.7 N/mm²

Curing rate: 2-3mm / 24hours

Tensile strength: 2.2 N/mm²

Tear strength: 12 N/mm

Service temperature range: - 40°C to +80°C

Slump: Non-sag

UV resistance: Good

APPLICATION

PROPERTIES

Application temperature range: + 5°C to + 40°C

Shelf life: 18 months

Skimming time: 20-40 minutes

Working time: 20-40 minutes

INSTRUCTIONS

Joint design: Please consult the Technical Information Sheet entitled 'Joint design for cartridge based products' prior to application.

Surface preparation: All surfaces must be clean, dry and free from frost, grease and loose materials. Apply primer if required. Most substrates only require priming if testing indicates it is needed. Apply using a skeleton gun into the joint ensuring good contact with surfaces. In situations where an especially neat finish is required, use masking tape to cover the face edges of the joint and remove immediately once tooling has been completed.

Tooling: Tool immediately after application, within the working time for the product.

EQUIPMENT

A selection of hand & air operated guns is available for cartridge and/or sausage application including a high power type especially suitable for filling deep voids.

PACKAGING

290ml cartridges – 25 per box. Colours: White, Grey & Black.

600ml foil sausages – 12 per box. Colours: White, Grey & Black.

HEALTH AND SAFETY

Non-flammable. Wash hands immediately after use.

See Product Safety Data Sheet for further information.

GENERAL

HS30 is part of a full range of speciality sealants designed for the professional user. For further information please contact our Customer Care Team or visit our Website.

The information given in this product data sheet is based on laboratory tests and experience which we believe to be correct. Properties quoted are typical and do not therefore constitute a specification. In view of the wide range and variability of substrates, we would advise that our product should be tested by the user to establish suitability for its intended application. E &OE.